

MIRASIL® CM5



Description	CTFA/INCI Name : CYCLOPENTASILOXANE CAS N° 541 – 02 – 6 EINECS N° 208-764-9 MIRASIL CM5 is a decamethylcyclopentasiloxane.																																												
Examples of applications	Antiperspirants, deodorants, hair care, skin care, perfumes.																																												
Advantages	<p>MIRASIL CM5 is a volatile carrier that provides a soft silky feel, and improves spreading properties for a wide range of personal care applications.</p> <ul style="list-style-type: none"> - Antiperspirants, deodorants : transient carrier for active salts. - Hair care: improves wet combing, yet leaves no residue. - Skin care: non- comedogenic emollient and carrier. - Perfumes: delivers fragrance and gives skin a smooth non-cooling feel. <p>Recommended use levels:</p> <p>Antiperspirants, deodorants: 3 – 10%.</p> <p>Hair care: 1 – 5% Skin care: 3 – 10%.</p> <p>Perfumes: 0.5 – 3%.</p>																																												
Characteristics	<table> <tbody> <tr> <td>Appearance.....</td> <td>Clear colourless liquid</td> </tr> <tr> <td>Colour, Hazen</td> <td>< 20</td> </tr> <tr> <td>Turbidity, NTU.....</td> <td>< 4</td> </tr> <tr> <td>Viscosity, at 25 °C, mm²/s, approx.....</td> <td>3.9</td> </tr> <tr> <td>Specific gravity at 25 °C, kg/m³, approx.....</td> <td>950</td> </tr> <tr> <td>Heavy metals, ppm Pb</td> <td>< 5</td> </tr> <tr> <td>Mineral oils, mg/kg</td> <td>< 0.1</td> </tr> <tr> <td>Refractive Index, 25 °C, approx.....</td> <td>1.395</td> </tr> <tr> <td>Surface tension at 25 °C, mN/m, approx</td> <td>18.3</td> </tr> <tr> <td>Odour</td> <td>None to slight</td> </tr> <tr> <td>Decamethylcyclopentasiloxane, %</td> <td>> 97.0</td> </tr> <tr> <td>Octamethylcyclotetrasiloxane, %</td> <td>< 0.9</td> </tr> <tr> <td>Decamethylcyclopentasiloxane + Dodecamethylcyclohexasiloxane, %.....</td> <td>> 99.7</td> </tr> <tr> <td>Acidity (in NaOH 0.01N, ml) for neutralization of 2 g product</td> <td>< 0.15</td> </tr> <tr> <td>Solubility in water, 0.1 g in 10 ml at 25 °C</td> <td>non miscible</td> </tr> <tr> <td>Solubility in pure ethanol at 25 °C (1.0 g in 10 ml).....</td> <td>miscible</td> </tr> <tr> <td>Cristallization point, °C, approx.....</td> <td>- 40</td> </tr> <tr> <td>Boiling point at 1013 mbar, °C, approx</td> <td>210</td> </tr> <tr> <td>Vapour pressure at 20 °C, kPa</td> <td>0.025</td> </tr> <tr> <td>Flash point (closed cup), °C, approx.....</td> <td>80</td> </tr> <tr> <td>Volatility evaporation rate (g/min), NF 30-302, at 80 °C</td> <td>0.075</td> </tr> <tr> <td>Volatility evaporation time (sec), DIN 53-170, at 23 °C</td> <td>8400</td> </tr> </tbody> </table>	Appearance.....	Clear colourless liquid	Colour, Hazen	< 20	Turbidity, NTU.....	< 4	Viscosity, at 25 °C, mm²/s, approx.....	3.9	Specific gravity at 25 °C, kg/m³, approx.....	950	Heavy metals, ppm Pb	< 5	Mineral oils, mg/kg	< 0.1	Refractive Index, 25 °C, approx.....	1.395	Surface tension at 25 °C, mN/m, approx	18.3	Odour	None to slight	Decamethylcyclopentasiloxane, %	> 97.0	Octamethylcyclotetrasiloxane, %	< 0.9	Decamethylcyclopentasiloxane + Dodecamethylcyclohexasiloxane, %.....	> 99.7	Acidity (in NaOH 0.01N, ml) for neutralization of 2 g product	< 0.15	Solubility in water, 0.1 g in 10 ml at 25 °C	non miscible	Solubility in pure ethanol at 25 °C (1.0 g in 10 ml).....	miscible	Cristallization point, °C, approx.....	- 40	Boiling point at 1013 mbar, °C, approx	210	Vapour pressure at 20 °C, kPa	0.025	Flash point (closed cup), °C, approx.....	80	Volatility evaporation rate (g/min), NF 30-302, at 80 °C	0.075	Volatility evaporation time (sec), DIN 53-170, at 23 °C	8400
Appearance.....	Clear colourless liquid																																												
Colour, Hazen	< 20																																												
Turbidity, NTU.....	< 4																																												
Viscosity, at 25 °C, mm²/s, approx.....	3.9																																												
Specific gravity at 25 °C, kg/m³, approx.....	950																																												
Heavy metals, ppm Pb	< 5																																												
Mineral oils, mg/kg	< 0.1																																												
Refractive Index, 25 °C, approx.....	1.395																																												
Surface tension at 25 °C, mN/m, approx	18.3																																												
Odour	None to slight																																												
Decamethylcyclopentasiloxane, %	> 97.0																																												
Octamethylcyclotetrasiloxane, %	< 0.9																																												
Decamethylcyclopentasiloxane + Dodecamethylcyclohexasiloxane, %.....	> 99.7																																												
Acidity (in NaOH 0.01N, ml) for neutralization of 2 g product	< 0.15																																												
Solubility in water, 0.1 g in 10 ml at 25 °C	non miscible																																												
Solubility in pure ethanol at 25 °C (1.0 g in 10 ml).....	miscible																																												
Cristallization point, °C, approx.....	- 40																																												
Boiling point at 1013 mbar, °C, approx	210																																												
Vapour pressure at 20 °C, kPa	0.025																																												
Flash point (closed cup), °C, approx.....	80																																												
Volatility evaporation rate (g/min), NF 30-302, at 80 °C	0.075																																												
Volatility evaporation time (sec), DIN 53-170, at 23 °C	8400																																												

MIRASIL® CM5

Characteristics (cont')	<p><i>Soluble in:</i> Ethyl, Butyl acetates, Ethanol, Isopropanol.</p> <p><i>Insoluble in:</i> Water and Ethylene Glycol.</p>
Packaging	<p>MIRASIL CM5 is available in:</p> <ul style="list-style-type: none">- 4 drums 195 kg / Pallet 780 kg- 1 Ton container- Tanker
Storage and shelf life	<p>When stored in its original unopened packaging, at a temperature below +40 °C, the MIRASIL CM5 may be stored for up to 36 months from the date of manufacture clearly marked on the packaging.</p> <p>Beyond this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.</p>
Safety	Please consult the Safety Data Sheet of MIRASIL CM5 .

The Soap Kitchen
Unit 8 Caddsdown Industrial Park, Clovelly Road, Bideford,
Devon EX39 3DX
Tel: 01237 420872 (+44 (0)1237 420872)
Email: it@thesoapkitchen.co.uk